



Visualizing the Precision of Solution IV:

Intrinsic Viscosity of 5 Polymer Samples


by Dual Differential Forced Flow Viscometry ... with 5 minutes prep time!

The Situation:


3 grades were found to be within specifications, 0.59 +/- 0.02 dL/g

2 grades were out of tolerance with IV values of 0.617 and 0.539, respectively.

Full Viscomogram in Overlay View: 10 Injections, 2 per sample



Zoomed View of the Plateau



Baseline Flow Stability (<0.2%)

